

WINDOW FILM PERFORMANCE DATA

FORMULAONE
WINDOW TINT



% Visible Light
Transmission

% Total Solar
Energy Rejection

% Ultraviolet
Protection
(wavelengths 300-
380nm)

% Glare
Reduction

% Visible Light
Reflection

CLASSIC™ SERIES

For long-lasting looks that enhance both style and appearance

Classic 05	5	44	>99	94	5
Classic 15	18	40	>99	79	5
Classic 30	33	36	>99	63	6
Classic 35	38	35	>99	57	6
Classic 50	60	28	>99	32	7

COMFORT™ SERIES

Superior heat and ultraviolet protection

Comfort 05	6	59	>99	93	8
Comfort 15	14	58	>99	84	8
Comfort 30	31	46	>99	65	7
Comfort 38	38	41	>99	57	7
Comfort 50	53	35	>99	40	8

PINNACLE® SERIES

Maximum heat protection without blocking electronic signal transmission

Pinnacle 05	5	64	>99	94	5
Pinnacle 15	19	60	>99	78	5
Pinnacle 30	33	56	>99	63	6
Pinnacle 35	38	55	>99	57	6
Pinnacle 40	43	53	>99	51	6
Pinnacle 50	55	50	>99	38	7

EASTMAN

LLumar.com



Performance data was captured using the National Fenestration Rating Council's (NFRC) standard guidelines for window film solar performance measurement as measured on single pane, 1/4 inch (6mm), clear glass. Reported values are taken from representative product samples and are subject to normal manufacturing variances. Actual performance will vary based on a number of factors, including glass type and properties. © 2016 Eastman Chemical Company. FormulaOne®, the FormulaOne® logo, LLumar® and the LLumar® logo are trademarks of Eastman Chemical Company or one of its wholly owned subsidiaries. As used herein, ® denotes registered trademark status in the U.S. only. Printed in U.S.A. (10/16) SP1117